

95 ABSTRACT OF THE DISCLOSURE

A process to eliminate or reduce the pre-reduction step for catalysts for nano-carbon synthesis by first, heating a metal oxide at 5°C/min to 350 - 500°C for 70-90 minutes under 10 - 20% hydrogen; optionally holding the
100 temperature for 10 to 60 minutes; then initiating carbonaceous feedstock flow.

P:\Greg\PATENTS\15630142.pat.app.wpd